

Elastron D100.A30.N

TECHNICAL DATASHEET

Product Description

A soft, colorable SBS based thermoplastic elastomer (TPE) compound designed for injection molding applications.

General Properties

ColorNaturalCertificationsRoHSProcessing MethodInjectionAvailable StandardsASTM

Physical Properties

Unit		Value	
SHORE A	ASTM D 2240	30	
g/cm³	ASTM D 792	1.09	
MPa		3	
MPa	ACTM D 442	0.40	
MPa	ASTMID 412	0.70	
%		900	
% @ 23°C 22 h		10	
% @ 70°C 22 h	ASTM D 395		
% @ 100°C 22 h			
mm³	ASTM D 1630		
HB, V ₀ , V ₁ , V ₂	UL 94		
N/mm	ASTM D 624	11	
	SHORE A g/cm³ MPa MPa MPa MPa % % @ 23°C 22 h % @ 70°C 22 h % @ 100°C 22 h mm³ HB, V ₀ , V ₁ , V ₂	SHORE A g/cm³ ASTM D 2240 g/cm³ ASTM D 792 MPa MPa MPa ASTM D 412 MPa % % @ 23°C 22 h % @ 70°C 22 h mm³ ASTM D 1630 HB, V ₀ , V ₁ , V ₂ UL 94	

Bondable to

PS,EVA,PE

Processing

Injection Molding Paramaters

Molding Temperatures	Temperature (°C)
Rear	140 - 150
Center	145 - 160
Front	150 - 165
Nozzle	165 - 185
Mold	25-50

ELASTRON Products are not compatible with PVC and Acetal.

Regrinding level up to %20 is recommended with minimum property loss.

Shrinkage			
	Value (%)	Test Standard	
Longitudinal Shrinkage	4,40	ASTM D955	
Cross Shrinkage	1,68	ASTM D955	

Notes

The properties shown are typical values and are not intented as product specifications. This statement is only valid for the product mentioned above. We can not guarantee for the final products due to addinitional processing at your plant which is not under our control.

ISO 9001:2008& ISO TS 16949 & ISO 14001 REGISTERED QUALITY SYSTEMS







FR.07.03.16 Rev.02