

ISO Property | LOTTE Advanced Materials

starex	Grade	SD-0150 W
	Resin Type	ABS

Item	Measuring Method	Condition	Unit	Value
Physical				
Specific Gravity	ISO 1183	Natural or representative color	-	1.04
Melt Flow Index	ISO 1133	200°C, 5kg	g/10min	2.2
Mechanical				
Tensile Strength at Yield	ISO 527	50mm/min	MPa	42
Izod Impact Strength (notched)	ISO 180 1A	at 23°C, 4mm	KJ/m ²	19
Rockwell Hardness	ISO 2039-2	R-scale	-	110
Thermal				
VICAT Softening Temperature	ISO R 306	B/50	°C	99

1. The value above is the representative value of the NP or representative color and may have deviation. It can only be used for selecting materials.
2. The value above shall not be regarded as a material specification and cannot be used for molding designs.

Information inserted in this document such as data, statements, representative values, etc. are provided solely for customer convenience. It does not expressly or impliedly guarantee anything regarding the safety or practicability of the (1) materials, (2) products, and/or (3) design that utilizes recommendations or proposals, of LOTTE Advanced Materials. Furthermore, nothing in the contents of this document shall have any legal binding effect, and especially, the representative value is simply for reference and is not a minimum value that has legal binding effect.

Whether materials and/or products of LOTTE Advanced Materials and/or a design that uses or utilizes LOTTE Advanced Materials' recommendations or proposals are (is) compatible with individual uses shall be determined solely by each user and such user shall be solely responsible for any results, including but not limited to, any and all loss and damages incurred due to such uses. Users must implement and verify all testing and analyses for proving the safety and compatibility of final products that have been created or altered by using LOTTE Advanced Materials' materials or products. The data and values inserted and/or contained in this document may be changed due to quality improvement of the product without any prior notification.

※ The last update date : 05/13/2014

UL Certification | LOTTE Advanced Materials

storex	Grade	SD-0150 W
--------	-------	-----------

iq.ul.com

Component - Plastics [\[guide info\]](#) E115797

Lotte Advanced Materials Co Ltd
56 Gosan-ro, Uiwang-si Gyeonggi-do 437-711 KR

SD-0150(+)
Acrylonitrile Butadiene Styrene (ABS), "STAREX", furnished as pellets

Color	Min Thk (mm)	Flame Class	HWI	HAI	RTI Elec	RTI Imp	RTI Str
ALL	1.0	HB	-	-	60	60	60
	1.5	HB	5	0	60	60	60
	3.0	HB	4	0	60	60	60
	6.0	HB	4	0	60	60	60

Comparative Tracking Index (CTI): 0
Dielectric Strength (kV/mm): 18
High-Voltage Arc Tracking Rate (HVTR): 1
Dimensional Stability (%): 0

Inclined Plane Tracking (IPT): -
Volume Resistivity (10^x ohm-cm): 16
High Volt, Low Current Arc Resis (D495): 7

(+) - May be replaced by one, two, or three numbers and/or letter(s)

ANSI/UL 94 small-scale test data does not pertain to building materials, furnishings and related contents. ANSI/UL 94 small-scale test data is intended solely for determining the flammability of plastic materials used in the components and parts of end-product devices and appliances, where the acceptability of the combination is determined by UL.

Report Date: 1988-06-03
Last Revised: 2013-04-01

© 2016 UL LLC

IEC and ISO Test Methods				
Test Name	Test Method	Units	Thk (mm)	Value
Flammability	IEC 60695-11-10	Class (color)	1.0	HB75 (ALL)
			1.5	HB75 (ALL)
			3.0	HB40 (ALL)
			6.0	HB40 (ALL)
Glow-Wire Flammability (GWFI)	IEC 60695-2-12	C	-	-
Glow-Wire Ignition (GWIT)	IEC 60695-2-13	C	-	-
IEC Comparative Tracking Index	IEC 60112	Volts (Max)	-	-
IEC Ball Pressure	IEC 60695-10-2	C	-	-
ISO Heat Deflection (1.80 MPa)	ISO 75-2	C	-	-
ISO Tensile Strength	ISO 527-2	MPa	-	-
ISO Flexural Strength	ISO 178	MPa	-	-
ISO Tensile Impact	ISO 8256	kJ/m ²	-	-
ISO Izod Impact	ISO 180	kJ/m ²	-	-
ISO Charpy Impact	ISO 179-2	kJ/m ²	-	-